

A GOOD SOLUTION!



Welding PVC strips: Quality, Technical details!

Density	DIN 53479/A	1,21 g/cm ³ ±0,02
Breaking point at low temp.	DIN 53372	ca. -35°C
Use temperature min.		-5°C
Use temperature max.		+60°C
Water absorption	DIN 53472	17mg 0,1%
Elongation at break	DIN EN ISO 527-2/5A/200	420%
Tensile strenght at yield	DIN EN ISO 527-2/5A/200	18 MPa
Further tensile strenght	DIN 53515	5 N/mm
Inflammability	DIN EN ISO 25980:2015-01	Heavily inflammable
Fire behaviour	DIN EN ISO 25980:2015-01	Go out by yourselves within 3 second
Sound barrier	DIN 52210	ca. 30dBa.
Hardness Shore A	DIN 53505	79±3
REACH conformity	We confirm compliance with the Regulation 1272/2008 of the European Parliament and the Council of 16.12.2008	

This certification is made by the DarTech, Based on the original certificate of conformity issued by the manufacturer.



DarTech L&L SRL

Adresa: Com. Mosnita Noua, Jud. Timis, Calea Medves Nr. 1001 Hala 2A
E-mail: office@dartechpvc.ro Tel: +4.0724.023.405